




Monument Chemical  
2450 Olin Road  
Brandenburg, KY 40108  
Email: [info@monumentchemical.com](mailto:info@monumentchemical.com)

---

## Sales Specification



## POLY-G HQEE®

---

<u>Property</u>	<u>Unit</u>	<u>Specification</u>	<u>Test Method</u>
Purity (diether)	wt%	90 Min	GC-102
Total Ethoxylated Hydroquinones	wt%	99 Min	GC-102
Ethylene Glycol Isopropyl Ether	wt%	0.15 Max	GC-102
Diethylene Glycol Isopropyl Ether	wt%	0.3 Max	GC-102
Hydroquinone	wt%	0.4 Max	GC-102
Water	wt%	0.1 Max	GP-2D
Yellowness	-	50 Max	GP-3B3
Alkalinity	µeq/g	0.7 Max	GP-4M2
Setting Point	°C	98.0 – 106.0	GP-61-C-1
Hydroxyl Number	mgKOH/g	545 – 565	GP-19E
Equivalent Weight (Calculated from OH Number)	-	Read & Report	-

**Product Code: 101376**  
**CAS Number: 104-38-1**  
**Synonym: 2,2'-(1,4-phenylenebis(oxy))bisethanol;**  
**hydroquinone bis (2-hydroxyethyl) ether**  
**Effective Date: 12/10/2018**  
**Revision: FCD-00181/12**

The information in this product specification sheet is made without warranty. Monument Chemical disclaims any liability in connection with the use of this information, and does not warranty against infringement by reason of the use of any of its products in combination with other materials in any process.